



TECHNICAL DATA SHEET SELLACK URETHANE SYNTHETIC METALLIC

Description: Glossy synthetic based urethane paint with high elasticity and good physical and chemical stability.

Physical properties:

Color: can be anything.

Gloss: 95-105 (60°)

Solid volume of 54% ± 1

Solid by Weight 53% ± 1

Theoretical coverage 10.92 m²/kg

Flash point < 23°C

Density 0.92 g/cm³ ± 0,02

Drying surface: 4 hours at 20°C

Touch dry: 12 hours (20°C)

Complete drying: after 7 days (20°C)

Thinner: Urethane Sentetik Tiner (10-15%)

Method of application: spray, airless, with roll

Areas of application:

Surface Preparation:

The surface must be dry and free of dust, grease, oil and other contamination. Waiting time between application of primer and intermediate layer must be considered.

Recommendations for application:

The temperature during application must be in the range 10°C - 35°C and relative humidity should be above 70%. The temperature of the paint itself during application should fall below 12°C. To prevent moisture forming surface temperature of the material must be 3°C above the dew point condensation. In confined spaces provide adequate ventilation during application and drying.

Application:

Stir and add ferrolite solvent for at least 10 min to form homogeneous.

Storage: The storage period is one year in a dry and cool place, undamaged packaging. Avoid exposure to direct product sunlight.