Colorificio Sammarinese SpA Via del Camerario 7 47891 Falciano, San Marino

T +378(0549)905 515 F +378 (0549) 908 453

colorificio@colsam.com colsam.com C.o.e. SM00026 Fully paid-up share capital € 3,000,000.00 Legal title no. 26 dated 20 May 1944



## 21000200

## PERFECTUM BIANCO

## masking waterborne paint for plasterboard



This is a professional ultra-washable, high opacity, matt, extra white and masking waterborne paint. Even if it has an extremely fine texture, it reduces and conceals fillings and joints thanks to its high filling power. Excellent for plasterboard, in most cases it covers the surface with a single coat and without fixative. A ready-for-use, single-coat product that helps to save time while guaranteeing excellent finishes for indoor environments.

Special dust-prevention, non-drip and anti-refraction additives facilitate application and visual appeal, even on the more sensitive parts such as ceilings and inclined surfaces. Minimises issues with reworking and touch-ups.

Specially formulated for interiors, it guarantees a particularly healthy living environment allowing it to be classified A+ according to the rigorous French standard 321/2011.





1

Date of revision

Composition Single-component, physically-drying, matt, vinyl-acrylic paint in aqueous dispersion for the

finishing coat, with classification according to UNI 8681: B4.C.O.A.2.HB

Main properties • covers with one coat

professional result

ready for use

04 June 2018

**Applications** For internal walls.

With its extremely fine texture, it reduces and conceals fillings and joints thanks to its high filling power. Perfect for all interiors and excellent for plasterboard, in most cases it covers the surface with a single coat and without fixative. Special dust-prevention, non-drip and anti-refraction additives facilitate application and visual appeal, even in the most sensitive areas, such as ceilings and inclined surfaces. High whiteness which enhances the

brightness in interior spaces.

**Colour** Bianco base, Colormaker bases.

Can be coloured with the Colormaker tinting system; the number of available bases is

indicated in the catalogue and in the Colormaker Lab software.

<b>Technical specifications</b> (data measured at 20°C, 65% R.H.)	Reference	Unit	Value
Specific weight (pycnometer)	C022		$1.500 \pm 0.050$
pH	C030		$8.5 \pm 0.5$
Brookfield viscosity	C054		$2,300 \pm 200$
Whiteness (instrumental)	C062		$84.00 \pm 2.00$
Grain structure	EN ISO 13300	μm	100 fine
Contrast ratio	EN ISO 13300		Class 2 (7 m <sup>2</sup> /l)

Colorificio Sammarinese SpA

Via del Camerario 7 47891 Falciano, San Marino

T +378(0549)905 515 F +378 (0549) 908 453

colorificio@colsam.com colsam.com

C.o.e. SM00026 Fully paid-up share capital € 3,000,000.00 Legal title no. 26 dated 20 May 1944



Resistance to brushing while wet

Dry-hard drying

Fire reaction on A1 and A2 surfaces Fire reaction paint only

EN ISO 13300

24-48 hours

Class 2

A2-s1, d0

EN 13501-1 EN 13501-1 B-s1, d0

Method of use

Ambient temperature min +5°C / max +35°C RH < 80%

. Surface and application conditions

Surface temperature min +5°C / max +35°C RH < 10%

. Application method

Brush, roller, airless.

. Thinner

Water

. Dilution Ready to use. Maximum dilution 15%

Mix the product with care, adding water gradually until you reach the correct viscosity. . Mixing

. Theoretical spreading rate 14-16 sq.m/l for each coat, depending on the absorbency of the surface.

Application cycle

**NEW SURFACES** 

Make sure that the surface is dry and clean, fill any cracks with Titanstucco. To enhance the wall's protection or in the presence of chalking surfaces, we recommend applying a fixative such as Titancril or White Fixative. Then apply PERFECTUM BIANCO as a

finishing coat.

PAINTED SURFACES

If the old paint is of good quality and firmly anchored to the surface, remove any dust and proceed as for a new surface. If the presence of old peeling or chalking paint, remove the detached parts, dust the surface and fill any cracks with Titanstucco, where necessary; if the surfaces are attacked by moulds, treat them with products of the Biosistem range.

Subsequently, proceed as you would for new walls.

**Notes** 

Any hardened drops can be easily removed with Diluente Nitro 92100012 thinner.

Storage

Do not allow to freeze; store at + 5°C to + 20°C. Once opened, the undiluted product can

be kept for 3 months in the closed container and in the dark.

Warnings

Wash brushes and tools immediately after use; do not dump the wash water on the ground

or into groundwater.

Keep out of reach of children.

For further information, consult the safety data sheet.

**VOC classification - Directive** 2004/42/EC - Italian Legislative Decree

161/2006

A/A -, maximum 30 g/I (2010).

Maximum VOC content of PERFECTUM BIANCO ready for use:

10.470 g/l.

Colorificio Sammarinese SpA Via del Camerario 7 47891 Falciano, San Marino

T +378(0549)905 515 F +378 (0549) 908 453

colorificio@colsam.com colsam.com

C.o.e. SM00026 Fully paid-up share capital € 3,000,000.00 Legal title no. 26 dated 20 May 1944



## Specification items

Apply 1 or 2 coats of 21000200 PERFECTUM BIANCO, the masking waterborne paint for plasterboard, in the colour chosen by the work supervisor, after suitable preparation of the surfaces to be treated. Including materials and application, excluding skimming and/or scaffolding.

This information is the result of our practical experience but is purely indicative. For more detailed information, please contact our technical support service. This sheet cancels and substitutes any previous editions.