

TIXE srl
Via Carlo Ferrari, 49
(Frazione Pratalborato)
15060 Capriata d'Orba (AL) IT
Phone +39 0143 46397



  
www.tixepaint.com
mail@tixepaint.com
Partita IVA IT 01779800992



Famiglia : TOP QUALITY

Product : GOLD PAINT FOR INDOOR

DESCRIPTION	Paint resin-based unsaponifiables, pigmented with bronze powders in different shades.
KEY FEATURES	<ul style="list-style-type: none">- Effect Leafing- High gloss- Large decorative
EMPLOYMENT	Treatment auction frames of wood, stucco, fillets and decorations of furniture, restoration of antique furniture, touches of brass objects, copper, or subjected to other treatments galvanic, showing discontinuity of treatment (in these cases is indicated spray pack).
APPLICATION	<p>The surface to be coated with silver TIXE must be prepared with appropriate treatment, namely:</p> <p>ON NEW MEDIA: For a better anchorage and greater length in time, the area must be thoroughly defatted with water and soap or diluter wash. Then a fund preparation and then one coat of product.</p> <p>MEDIA ALREADY ON 'Paint: if the existing layer of paint does not recommendations to the complete removal, degreasing with water and detergent and rinse.</p> <p>If the existing paint is in the process of posting brushing and sanding to the bottom these parts, or to paint stripping with paint strippers. Wash with diluent by washing with water or soap and then apply a fund preparation and a hand of the product.</p> <p>Use the following funds preparation: For iron: rust type paintable nitro. Wood: sottosmalto paintable sized nitro or nitro. Surface plaster and stucco: nitro sized hand or bottom paintable nitro.</p> <p>During the application by brush or roller not cross the hand, and not pull the product, but leave a fairly large film to promote the formation of the metallic mirror. Avoid applying a second-hand, which would remove the previous year, undermining the formation of the mirror finish, which is the prerogative of a typical 'GOLD PAINT TIXE. Recommended applications: a brush, roller, dipping, spraying, airless.</p> <p>For dusting the surface with GILDING TIXE, use a soft cloth, gently used.</p> <p>The process is ONLY and ONLY recommended for internal use. We do not recommend APPLICATION OUTSIDE, as GOLD PAINT TIXE is susceptible to rapid oxidation and consequent darkening when exposed to moisture and / or aggressive.</p> <p>Conditions and media: The support must be dry, dust-free and grease and any other substance</p>

TIXE srl
Via Carlo Ferrari, 49
(Frazione Pratalborato)
15060 Capriata d'Orba (AL) IT
Phone +39 0143 46397



  
www.tixepaint.com
mail@tixepaint.com
Partita IVA IT 01779800992



pollutant
Temperature: min. 10 ° C / max 35 ° C
Relative humidity of <75%
Temperature of medium: min. 10 ° C / max 35 ° C

DILUTION

The product is to be used as such.

Given the nature of the pigment, consisting of flakes of bronze, there is a strong tendency of the metallic pigment to settle.

It is therefore recommended that a thorough mixing of the product before and during application, so as to ensure the continued consistency of the product.

STORAGE

In a cool and well ventilated.
Keep the jar tightly closed, upside down and away from frost and heat.

PHYSICAL CHARACTERISTICS (at 20 ° C and 50% - 60% RH)

Specific gravity 0.985 0.02 kg / L.

3 "Cup 2 ISO±Time of outflow 14

Yield (*) 08 - 10 Mq / Kg

1 hour drying off mark
5 hours in-depth

Colour ORO DUCAT, PALE, RICH, RICH PALE,
SEQUIN, COPPER.

Storage life of at least 36 months

(*) The yield depends on the nature and porosity of the surface.

VOC CLASSIFICATION

Product free from VOC regulations 2004/42

PRECAUTIONS

In addition to reports of the risk and precautions governing the GOLD PAINT TIXE in the form of production and which are listed on the container, you should, before making the application of the product, see its data sheet.

It 'still a good idea to use gloves and goggles, and make the application in a well ventilated.