

TECHNICAL DATA SHEET



SEAM SEALANT

Thixotropic sealant based on solvent for joints and overlaps for application with a brush or spatula. Can be used on flanged or welded metal in the front and rear parts of the car body, the boot compartment, on the floor and the inside of the floor panel.

Seam Sealant RANAL dries quickly; drying can be speeded up at a higher temperature. Once cured, it does not break and is an ideal barrier for water and moisture

FOR PROFESSIONAL USE!

APPLICATION AND USE:

The sealant must be applied on clean surfaces free of dust.

Cover the surface of metal with an anti-corrosion primer, after drying apply the sealant. If necessary, the product can be over coated before it dries completely.

CONTENT OF VOLATILE ORGANIC COMPOUNDS:

VOC II/B/d= 840g/L, VOC = 360 g/L

SURFACE DRYNES OF THE COATING (25°C, RELATIVE HUMIDITY 55%):

3 – 4 min.

COMPLETE DRYNESS OF THE COATING (25°C, RELATIVE HUMIDITY 55%):

24 h (1 mm thick)

VISCOSITY AT 25°C:

250.000 – 350.000 cps

SPECIFIC WEIGHT:

1,20 ± 0,02 g/cm³

OVERCOATING AT 25°C, RELATIVE HUMIDITY 55%:

after 24 h (when completely dry)

TECHNICAL DATA SHEET

APPEARANCE:

Thixotropic paste.

APPLICATION TEMPERATURE:

15°C ÷ 35°C

COLOUR:

Light grey.

TOOLS CLEANING:

Thinner for nitrocellulose or acrylic products.

STORAGE CONDITIONS:

Store in a dark and dry place away from the sources of fire and heat. Shelf life of the product in original package at +20°C is 18 months from the date of production.

HEALTH AND SAFETY RECOMMENDATIONS:

According to Safety Data Sheet of Dangerous Substance for particular product.

PACKAGING:

Art. No	Capacity	Package, pieces:	Package weight, kg
20432-1	1kg	12	14,10

This information is based on careful laboratory research and many years of experience. Strong market position does not absolve us from constant control of the quality of our products. However, we are not responsible for the final results after incorrect use of the product.