

TECHNICAL DATA SHEET**ONE-COMPONENT ACRYL FILLER
SPRAY**

High quality one-component acrylic filler of very short drying time. Designed for surface preparation on car body elements. This product is suitable under all acrylic coats, easily sandable on wet (recommended paper P800) and dry (recommended paper P500-P600), efficient and resistant to scratches.

IT CAN BE USED ON THE FOLLOWING GROUNDS

Unprocessed surfaces of:

- ◆ Wood
- ◆ glass
- ◆ metal
- ◆ stone
- ◆ plastics

Attention! In case of plastic surfaces of poor adhesion use Adhesion Increasing Agent RANAL.

PRODUCT CHARACTERISTICS

- ◆ Very good adhesion to various ground types.
- ◆ Very thorough covering of a surface.
- ◆ Possible use inside as well as outside.
- ◆ Odourless gases used.

INSTRUCTION FOR USE

- ◆ Sand the surface with P600 paper before use.
- ◆ Clean, dry and degrease the surface before application.
- ◆ Shake carefully the container before use for about 3 min.
- ◆ Apply 2-3 single coats from the distance of about 30 cm.
- ◆ Make 5-10 min. pauses between the applications of the coats.
- ◆ Clean the nozzle after use, by putting the container upside down and pressing it for 5 seconds.

ATTENTION! It is best to paint in a dry room in the temperature of 20°C.

TECHNICAL DATA SHEET**DRYING TIME**

Dust free: 15 min.

Touch dry: 30 ÷ 40 min.

Completely dry: 24h

THEORETICAL EFFICIENCY

400 ml of the filler is enough to cover about 2,0 - 2,5 m² of a surface.

CONTENT OF VOLATILE ORGANIC COMPOUNDS

II/B/e limit = 840 g/l, VOC = 640 g/l

STORAGE CONDITIONS

Store in a dark and cool place away from fire and heat sources. The shelf life in original package in the temperature of 20°C is 60 months.

HEALTH AND SAFETY RECOMMENDATIONS

According to Material Safety Data Sheet of Dangerous Substance for particular product.

PACKAGING

Art. No	Capacity, ml	Package, pieces.:	Package weight, kg:
10710 [white]	400	12	5,40
10703-1 [grey]	400	12	5,40
10711 [black]	400	12	5,40

This information is based on careful, laboratory research and our long-standing experience. Strong market position does not absolve us from constant control of the quality of our products. However, we are not responsible for the final results after incorrect use of the product.