

LEGNODUR 4701

DESCRIPTION

Poliacetovinylic homopolymer dispersion-pure free plasticizers, fast setting adhesive particularly suitable for gluing hardwoods, in particular for difficult bonding of chairs.

TECHNICAL CHARACTERISTICS

Solid content 50% Particle Size 05/3+7°C MFFT (min. film form. Temp.) + 15 ° C Suggested temp. room and work Film aspect turbid Colour yellowish Grammage 130 / 170 / sqm Open time on glass 8/10' PH at the origin 4.5 / 6

PH at the origin
4.5 / 6
Frost resistance
Medium seal resistance of adhesive
200 kg / scm

PRECAUTIONS

Keep from freezing store at +5 ° C

PACKAGING

Can 1 kg

Bucket 5-10-20 Kg

Tank 25 Kg

Drum 120 – 200 Kg IBC Cont. 1.000 Kg

RECOLL INTERNATIONAL srl guarantees that the information in the present sheet are given to the best of its experience and technical-scientific knowledge; however, it is not liable for results obtained as application conditions are out of its control. It is recommended to always verify the suitability of the product for the specific case. The present sheet annuls and substitutes any previous sheet.