



Test Report

The classifications of the requested products according to EN 13300 standards are given in the table.

Sample Name : **Betek Max White**
: **Betek Sil White**
: **Betek Satin White**

The date of documenting : 26.03.2021

Results of Analysis

Product Name					Betek Max White	Betek Sil White	Betek Satin White
Test Name	Standard	Period	Caption	Unit			
Density	TS EN ISO 2811-1			g/ml	1,42±0,03	1,29±0,03	1,38±0,03
Viscosity (Haake)	TS 5808	---		Pa	300-360	150-240	170-220
Determination of PH Value	TS 5808				7-9	7-9	7-9
Hiding Power-Waterbased				%	2. Class	2. Class	2. Class
Brightness - Waterbased Interior Paint	EN 13300		60°	Gloss	2-5	5-8	15-20
Brightness - Waterbased Interior Paint			85°	Gloss	10-15	45-50	75-80
Brightness - Waterbased Interior Paint				Class	Semi Gloss	Semi Gloss	Semi Gloss
Wet Scrub Resistance		After 28 Days	200 Cycles		µm	1.Class	1.Class

Seal

BETEK
BOYA VE KİMYA SAN. A.Ş.
Büyük Mükellefler Y.D. 167 001 2389
Tel: (0216) 571 10 00

Date
26.03.2021

Manager of Water Based Coatings R&D
Mesut EREN

This report shall not be reproduced other than in full except with the permission of Betek Laboratory
Testing reports without signature and seal are not valid.