

**TWO-COMPONENT MOISTURE-REPELLENT EPOXY PRIMER FOR CONCRETE - REAL WET 365**

**PRODUCT DESCRIPTION**

**REAL WET 365** is a two-component, solvent-free epoxy resin based, epoxy moisture tolerant primer that creates a moisture barrier for 30% moisture and wet surfaces and penetrates into capillary cracks in concrete.

**TECHNICAL SPECIFICATIONS**

Appearance	Blurry
Color	Brown
Density (gr./ml. 20°C)	1.15 ± 0,05
Mixing Ratio (by Weight)	Comp.: A 7,2 unit Comp.: B 2,8 unit
Solids by Weight (w/w)	% 98 ± 2
Application Method	Trowel, Brush, Roller
Pot Life (20°C)	20-25 min.
Full Curing (day/20°C)	4-6 day



**DRYING INFORMATION (100 micron KFK)**

	Touch Dry	Hard Drying	Waiting Times Between Floors (Minimum)
<b>-5°C</b>	12 hour	29-30 hour	24 hour
<b>0°C</b>	9 hour	20-21 hour	18 hour
<b>5°C</b>	6 hour	13-14 hour	12 hour
<b>15°C</b>	120-160 min	5-6 hour	3.5 hour
<b>25°C</b>	80-100 min	3-4 hour	2 hour
<b>35°C</b>	60-80 min	1.5-2 hour	1,5 hour

**NOTE:** As the application thickness increases, the drying time also

CONSUMPTION Wet Film Thickness ( $\mu$ )	Dry Film Thickness ( $\mu$ )	Theoretical consumption rate for 8 mm stone carpets $\pm 10$ (kg./m <sup>2</sup> )
<b>260</b>	<b>234</b>	<b>0,300</b>

**NOTE:** As the application thickness increases, consumption also increases.

## APPLICATION AREAS AND FEATURES

**REAL WET 365** damp surface concrete primer

**REAL WET 365** usage areas;

It is used as a concrete primer on surfaces with up to 30% moisture before the application of epoxy, polyurethane, self-leveling screed and polyurea in factory and warehouse floors, work areas, loading areas, industrial floors exposed to medium and heavy loads.

## USAGE

### Surface Preparation

The application surface is carefully cleaned of dirt, oil and grease. Loose old paint (on previously painted surfaces) is cleaned. Rust and burrs on the surface are cleaned using a diamond-tipped machine according to SA 2 ½ standards. A mask must be used during applications using spraying. Very good ventilation is required, especially in small, closed areas.

### Use of the Product

**REAL WET 365** Before use, the components are mixed separately and thoroughly. Then, a homogeneous mixture is made with its own hardener. The product temperature should be 20-35°C..

Application method is by brush, roller or gun. A mask must be used in applications made by spraying.

## ENVIRONMENTAL CONDITIONS

The ambient temperature should be between +15°C and 35°C. Application should not be done when the relative humidity exceeds 80%. The surface temperature should be at least 3-5°C above the dew point to prevent surface condensation.

It should be noted that consumption will increase in applications at low temperatures. The surface temperature should be at least +5°C and at most 45°C..

## PACKING

### REAL WET 365 :

Component A: 11,5 kg. & Component B: 4,5 kg.

TOTAL SET WEIGHT 16 kg.

-

### REAL WET 365 :

Component A: 3,6 kg. & Component B: 1,4 kg.

TOTAL SET WEIGHT 5 kg.



**SHELF LIFE**

The material should be stored in its original packaging in a cool and dry place. The storage life of the material in unopened packaging is 24 months for components A and B..

**HEALTH AND SAFETY INFORMATION**

- Read the MSDS form (Material Safety Data Sheet) for necessary safety rules and warnings. The minimum security rules to be followed are as follows.
- Contact of the product with skin and eyes should be prevented by using gloves, protective glasses, face mask and industrial cream.
- Adequate air circulation must be provided during application and until the paint dries.
- If the product comes into contact with the skin, it should be washed with warm water and soap or industrial cleaner. If it splashes into the eyes, it should be washed with water for at least 10 minutes and medical help should be sought.
- All warning notes on the bucket should be read carefully and the recommended operating rules should be followed.

\*Our information about the products is prepared based on our own laboratory tests and research under normal conditions. Our company is not responsible for the work done under inappropriate application conditions. Our company reserves the right to change this information. For more detailed information, please contact R.Y.K.

Rev. No:09/Rev.Date: October 2022



[www.adacolor-bg.com](http://www.adacolor-bg.com)

Sofia 6 "Andrey Germanov" str. mobile: 089 666 3042 / 089 468 3880	Sofia, "Ovcha Kupel 1" quarter 33 "Promishlena" str., 429 bl., store 18, mobile: 089 666 9071	Plovdiv 176 "Brezovsko shose" str. mobile: 089 544 7503 / 089 666 3044	Varna 25 "Usta Kolyu Ficheto" str. mobile: 089 666 9079 / 089 466 9023
Shumen, "Dobrudzhanski" quarter Ind.zone, "Stroykomplekt" site mobile: 089 455 1685 / 089 666 3043	Kardzhali 1 "Klokotnitsa" str. mobile: 089 575 0749 / 089 666 3057	Troyan 49 "Makedoniya" str. mobile: 089 666 9079 / 089 673 4489	Haskovo, 5 "Okolovrasten pat" str. South Industrial zone mobile: 089 666 3051 / 089 241 2833