



# THREE-COMPONENT EPOXY REPAIR COMPOUND FOR EXPANSION JOINTS AND CRACKS REAL GR 900

## PRODUCT DESCRIPTION

**REAL GR 900** is a three-component, high-strength epoxy repair compound designed for the repair of expansion joints, as well as the restoration and rehabilitation of damaged concrete floors. The product offers high mechanical strength, excellent adhesion to concrete substrates, and outstanding resistance to vibrations and impacts.

## TECHNICIAL SPECIFICATIONS

Appearance	Matte
Color	Brown
Density (gr./ml. 20°C)	1,80 ± 0,05
Mixing ratio by weight	Comp.: A 2,35 units Comp.: B 0,9 units Comp.: C 6,75 units
Solids by weight (w/w)	% 1,25 ± 2
Application method	Trowel
Open working time at +20°C	20-25 min.
Full drying at +22°C	4-10 days
Flexural strength	30 N/mm <sup>2</sup> (7 days) (TS EN 196-1)
Compressive strength	75 N/mm² (7 days) (TS EN 196-1)
Shore D hardness	83 (7 days)
Continuous Thermal Endurance	+50°C + 80°C (most 7 days)

## **APPLICATION AREAS AND FEATURES.**

**REAL GR 900** is used for filling and repairing expansion joints, as well as for the restoration and repair of damaged concrete floors.

## REAL GR 900 areas of use:

It is used as a repair material for floors in both indoor and outdoor areas. This is a three-component, self-leveling, solvent-free mortar consisting of a combination of specially graded aggregate materials and high-strength epoxy resins. When mixed, it forms a liquid, self-leveling epoxy grout.

## **ENVIRONMENTAL CONDITIONS**

The air temperature should be in the range of +15°C to +35°C. Application should not be carried out when the humidity exceed 80%. The surface temperature must be at least 3–5°C above the dew point to prevent condensation.

It should be noted that material consumption will increase when applied at lower temperatures. The surface temperature must be at least +5°C and no more than +45°C.





## USAGE

## **Surface Preparation**

The surface for application must be dry and carefully cleaned of contaminants such as dust and other.

## **Product Usage**

REAL GR 900 is used on all cracked and damaged reinforced concrete surfaces.

Application Method: The required amount of joint sealant is determined by the user and applied according to the type and size of the joint or the crack.

## PACKAGES

One package REAL GR 900 contains three components:

Component A: 0.420 kg. + B: 0.200 kg. + C: 4.38 kg. Total set weight: 5 kg.

Component A: 1.67 kg. + B: 0.830 kg. + C: 17.50 kg. Total set weight: 20 kg.



## SHELF LIFE

The material must be stored in its original packaging in a cool and dry place. The shelf life in unopened packaging is 24 months for components A, B and C.

## HEALTH AND SAFETY INFORMATION UCTION CHEMICALS

Refer to the product's Material Safety Data Sheet (MSDS) for safety guidelines and warnings.

The most essential safety precautions to follow are:

Contact of the product with skin and eyes must be avoided by using gloves, safety goggles, a face mask, and protective cream.

Ensure proper ventilation during application and until the primer is fully dried.

In case of skin contact, wash the affected area with warm water, soap, or a suitable cleanser.

In case of eye contact, rinse thoroughly with water for at least 10 minutes and seek medical attention.

Carefully read all warning labels on the packaging and strictly follow the recommended working

\* Our information about the products is based on our own laboratory tests and researches under normal conditions. Our company is not responsible for studies under unsuitable application conditions. The right to change this information is reserved by our company. Please contact R.Y.K. for more detailed information

Rev. No:09/Rev.Date: October 2022





• Life In Colors • www.adacolor-bg.com				
Sofia	Sofia, "Ovcha Kupel 1" quarter	Plovdiv	Varna	
6 "Andrey Germanov"str.	33 "Promishlena" str., 429 bl., store 18,	176 "Brezovsko shose" str.	25 "Usta Kolyu Ficheto" str.	
mobile: 089 666 3042 / 089 468 3880	mobile: 089 666 9071	mobile: 089 544 7503 / 089 666 3044	mobile: 089 666 9079 / 089 466 9023	
Shumen, "Dobrudzhanski" quarter	Kardzhali	Troyan	Haskovo, 5 "Okolovrasten pat" str.	
Ind.zone, "Stroykomplekt" site	1 "Klokotnitsa" str.	49 "Makedoniya" str.	South Industrial zone	
mobile: 089 455 1685 / 089 666 3043	mobile: 089 575 0749 / 089 666 3057	mobile: 089 666 9079 / 089 673 4489	mobile: 089 666 3051 / 089 241 2833	

