

e-4+1 Primer

HS 2K Acrylic Primer

Field of application	Passenger cars and commercial vehicles. New or repaired vehicle parts and complete priming of vehicles
Chemical bases	2-Component high quality hydroxy acrylic resin
General qualities	e-4+1 Primer HS 2K Acrylic Primer is a high solids, two component, easy to apply 4+1 acrylic primer with very good filling power and adhesion properties. It does not absorb the paints applied on it and provides long life to the topcoats. Colorable with P-Acryl Solid Color Top Coat.
Auxiliary materials	e-Fast/Standard/Slow Hardeners, a-Fast/Standard/Slow Hardeners and T 8-18/18-25/25-35/35+ Universal Thinners.
Mixing ratio (volume)	4:1 (4: e-4+1 Primer HS 2K Acrylic Primer, 1: e or a line hardeners) if needed add max. 10 % Universal thinners.
Gloss	Matt
Economy	Approx. 8 m ² /L/60 µm
Substrates	Applied on sanded and cleaned fully cured old coatings and plastic surfaces coated with plastic primer.
Undercoats	Irrelevant
Finishing materials	All Polaron Finishes.
Cleaning the equipment	Universal Acrylic Thinners and Cleaning Thinners
Colour	Grey, White and Black.
Storage life	Under normal storage conditions and unopened tins up to 2 years.

For professional use only. The technical information in this document has been carefully selected and prepared by us based on the current information. However, these data represent symbolic values. Since application variables are an important factor in product performance, this information should only be presented as a general guide. Polaron assumes no liability or responsibility for the use of this information. Due to any defect / error in this product, only the options of replacing the defective product or refunding the sales price are available, and the right to choose among them belongs to Polaron. See SDS for safety information.

e-4+1 Primer

HS 2K Acrylic Primer

APPLICATION DATA



Mixing ratio

4:1 (4: e-4+1 Primer HS 2K Acrylic Primer, 1: e or a line hardeners) if needed add max. 10% universal thinners.



Application viscosity

18-22 sec. (DIN CUP 4 mm/20 °C)



Gravity feed

Spray nozzle (mm)

Pressure (bar)

Suction feed

1.4-1.8

3.5-4.5

HVLP/LVLP

1.6-1.8

3.5-4.5

see info

manufacturer



Spray coats/
Coat thickness

1-3
60-180 µm



Flash-off time

5-10 min.



Drying

20 °C 2-3 hours per layer
60 °C 20 min.

20 °C Thin coat application, wet on wet can be made after 20 minutes. On thick coats, it should be applied after 16 hours.



Pot life

45-60 min. (in combination with e-Hardener Standard and a-Hardener Standard)
30-35 min. (in combination with e-Hardener Fast and a-Hardener Fast)



Safety

Use suitable respiratory protection (fresh air supply respirator is strongly recommended).
For more detailed information please see Safety Data Sheet.

For professional use only. The technical information in this document has been carefully selected and prepared by us based on the current information. However, these data represent symbolic values. Since application variables are an important factor in product performance, this information should only be presented as a general guide. Polaron assumes no liability or responsibility for the use of this information. Due to any defect / error in this product, only the options of replacing the defective product or refunding the sales price are available, and the right to choose among them belongs to Polaron. See SDS for safety information.



гр. София
ул. „Андрей Германов“ 6
GSM: 089 666 3042 / 089 468 3880

гр. София, кв. Овча Купел 1,
ул. „Промислена“ 33, бл.429, маг. №18
GSM: 089 666 9071

гр. Пловдив
ул. „Брезовско шосе“ 176
GSM: 089 544 7503 / 089 666 3044

гр. Варна
ул. „Уста Кольо Фичето“ 25
GSM: 089 666 9079 / 089 466 9023

гр. Шумен, кв. Добруджански,
инд. зона: база на Стройкомплект
GSM: 089 455 1685 / 089 666 3043

гр. Кърджали
ул. „Клокотница“ 1
GSM: 089 575 0749 / 089 666 3057

гр. Троян
ул. „Македония“ 49
GSM: 089 666 9079 / 089 673 4489

гр. Хасково, Южна индустриална
зона, ул. „Околовръстен път“ 5
GSM: 089 666 3051 / 089 241 2833

For professional use only. The technical information in this document has been carefully selected and prepared by us based on the current information. However, these data represent symbolic values. Since application variables are an important factor in product performance, this information should only be presented as a general guide. Polaron assumes no liability or responsibility for the use of this information. Due to any defect / error in this product, only the options of replacing the defective product or refunding the sales price are available, and the right to choose among them belongs to Polaron. See SDS for safety information.