

# JOINT FOR GYPSUM BOARD



## APPLICATION AREAS

It is applied to fill the connections between the individual panels of plasterboard or along their edges.

## PRESUPPOSITIONS

Its small fraction allows for uniform application and smoothes surfaces. Since it is an extremely flexible material, cracks will not occur at the joints.

## PACKAGING

Polypropylene lined bag 30kg  $\pm 2\%$

## STORAGE

Store in the manufacturer's packaging, in a closed package, on a pallet.

## TECHNICAL SPECIFICATIONS

Dilution: 7 l. water, 10 kg grout. Operating time: 80 minutes. Curing time: 170 minutes. Shrinkage force: min. 25 kg f/cm<sup>2</sup> Consumption rate: suspended ceiling, 0.2 kg/m<sup>2</sup> ; dividing wall, 0.6 kg/m<sup>2</sup>

## LAYING CONDITIONS


The temperature in the laying room should be min. +5°C. The surface to be treated must be free of dust, greasy stains, etc.

## HOW TO USE

Tape the places where the individual panels intersect. The grout is applied with pressure, with a trowel. The remnants of the grout are smoothed out with a trowel. It is applied with a metal trowel on the desired surface. The first panel is covered with a 10 cm distance from the edge/edges and only after finishing with this panel is the next one passed. To avoid contact with the plaster, the second layer is laid with a distance of 20 cm. If necessary, additional filling of the inter-joint space is carried out.

## SOLUTION PREPARATION

Pour water according to the amount of grout (ratio: 10 kg of grout to 7 liters of water) and add grout. Wait two minutes for the mixture to "ripen" and add more water. For better homogeneity, use a machine mixer. After stirring, the mixture is ready to use. The resulting mixture should be used within 80 minutes.





[www.adacolor-bg.com](http://www.adacolor-bg.com)

Sofia 6 "Andrey Germanov" str. mobile: 089 666 3042 / 089 468 3880	Sofia, "Ovcha Kupel 1" quarter 33 "Promishlena" str., 429 bl., store 18, mobile: 089 666 9071	Plovdiv 176 "Brezovsko shose" str. mobile: 089 544 7503 / 089 666 3044	Varna 25 "Usta Kolyu Ficheto" str. mobile: 089 666 9079 / 089 466 9023
Shumen, "Dobrudzhanski" quarter Ind. zone, "Stroykomplekt" site mobile: 089 455 1685 / 089 666 3043	Kardzhali 1 "Klokotnitsa" str. mobile: 089 575 0749 / 089 666 3057	Troyan 49 "Makedoniya" str. mobile: 089 666 9079 / 089 673 4489	Haskovo, 5 "Okolovrasten pat" str. South Industrial zone mobile: 089 666 3051 / 089 241 2833