DECORATIVE GYPSUM

APPLICATION AREAS

Gypsum for making decorative cornices for

STANDARD

TS 370, Plain Plaster (NA)

PACKAGING

Polypropylene lined bag, 30 kg ±2%

STORAGE

To be stored in the packaging of the S&P 500, it must be clean from the manufacturer, in a closed package, from dust, greasy stains, etc. on a pallet.

PRESUPPOSITIONS

The fraction is thin, for this reason, when laying, the surface is smoothed. The quality increases after hardening. Reduces the volume of losses to a minimum.

LAYING CONDITIONS

Before laying the moldings, the boards must be completely dry. The temperature in the laying room should be min. +5°C. The surface to be treated must be free of dust, greasy stains, etc.

TECHNICAL SPECIFICATIONS

Dilution: 7 I. water, 10 kg gypsum mixture

Curing time: 25 minutes

Shrinkage force: min. 70 kg f/cm² Thermal conductivity: max. 0.35

W/mk

Curing on dry surfaces: min. 60 props D

SOLUTION PREPARATION


Pour water into a clean container according to the amount of solution (ratio: 10 kg of gypsum mixture for cornice to 7 liters of water) and add the material. Wait two minutes for the mixture to "ripen" and add more water. For better homogeneity, use a machine mixer. After stirring, the mixture is ready to use. The resulting mixture will set within 25 minutes.

HOW TO USE

Pour into a template and leave to dry (set). The technical specifications must be adjusted to the working space, climatic conditions and the laying surface.



таван





www.adacolor-bg.com

Sofia
6 "Andrey Germanov"str.
mobile: 089 666 3042 / 089 468 3880

Sofia, "Ovcha Kupel 1" quarter 33 "Promishlena" str., 429 bl., store 18, mobile: 089 666 9071

Plovdiv 176 "Brezovsko shose" str. mobile: 089 544 7503 / 089 666 3044 Varna 25 "Usta Kolyu Ficheto" str. mobile: 089 666 9079 / 089 466 9023

Shumen, "Dobrudzhanski" quarter Ind.zone, "Stroykomplekt" site mobile: 089 455 1685 / 089 666 3043

Kardzhali 1 "Klokotnitsa" str. mobile: 089 575 0749 / 089 666 3057 Troyan 49 "Makedoniya" str. mobile: 089 666 9079 / 089 673 4489 Haskovo, 5 "Okolovrasten pat" str. South Industrial zone mobile: 089 666 3051 / 089 241 2833