



Acrylic HS primer 4:1

HIGH BUILD

Two-component acrylic primer with very good filling properties. A product of increased hardness, perfectly adhering to steel, well sandable and easy to process. It has very good filling properties. The ideal substrate to guarantee the perfect appearance of topcoats.

RANAL®

FOR PROFESSIONAL USE!

SUBSTRATE:

- ◆ old paint coats including z thermoplastic paints,
- ◆ polyester fillers,
- ◆ steel,
- ◆ galvanized steel,
- ◆ aluminium,
- ◆ plastics,
- ◆ polyester laminates,
- ◆ epoxy primers,
- ◆ reactive primers (wash primers).


GROUND PREPARATION:

- ◆ old paint coats should be degreased and dry sanded with P220 - P360 paper, dusted off and degreased,
- ◆ polyester fillers should be dry sanded with P240 – P320 paper for final smoothing, dusted off and degreased
- ◆ steel surfaces should be degreased and dry sanded with P120 - P240 paper, dusted off and degreased
- ◆ aluminium surfaces should be degreased and matted with an abrasive cloth, and degreased again,
- ◆ galvanized surfaces should be degreased and matted with a very fine abrasive cloth, dusted off and degreased again,
- ◆ stainless steel should be degreased,
- ◆ plastic surfaces should be wiped with Silicone Remover RANAL and with an abrasive cloth. Degrease again and apply Adhesion increasing agent and Elasticity increasing agent RANAL
- ◆ polyester laminates should be degreased and dry sanded with P280 paper, dusted off and degreased.

TECHNICAL DATA SHEET

RANAL®

MIXING RATIO:



	By volume	By weight
Primer	4	100
Hardener	1	15
Thinner	15% - 20%	6 - 11


ATTENTION!

- ◆ Acrylic thinner RANAL is recommended.
- ◆ Pot life of the mixture of primer and hardener is 1h.

INSTRUCTION FOR USE:

Mix the components carefully before application. Apply 2 - 3 wet layers, each 50-60µm thick, with evaporation time of 5-10 min. after each layer. Evaporation time depends on the temperature and layer thickness. 10 minutes after the application of the last layer the coat can be cured at higher temperature.

SPRAYING VISCOSITY:



Filling system:

15% Acrylic thinner RANAL
DIN 4/20°C app. 35-40s, Ø 1.6-1,8mm, 3-4 bar

Priming system:

20% Thinner for primers and bases RANAL
DIN 4/20°C app. 23-26, Ø1,6-1.8mm, 3-4 bar


SPRAY GUN NOZZLE, WORKING PRESSURE:

Ø1.6-1.8mm, 3-4 bar




ATTENTION! Layer thickness app. 50 – 60 µm of each one.

EVAPORATION TIME:



5 – 10 min.

DRYING TIME:



At the temperature of 20°C: 3 hours
At the temperature of 60°C: 30 min., for the thickness of 150-180 µm

SANDING:



Dry mechanical sanding: P360 – P500
Dry manual sanding : P400 – P500



Wet mechanical sanding: P600 – P1000
Wet manual sanding: P800 – P1000

CONTENT OF VOLATILE ORGANIC COMPOUNDS:

VOC category: II/B/c= 540 g/L, VOC = 510-540 g/L

AVAILABLE COLOURS:

Grey, Black, White

THEORETICAL PERFORMANCE:1 litre of the primer allows obtaining app. 6 m² of a dry film 120 µm thick.**TOOLS CLEANING:**

NITRO or Thinner for acrylic products RANAL

STORAGE CONDITIONS:

Store in a dark and dry place away from the sources of fire and heat. The shelf life in original package at 20°C is 24 months from the date of production for the primer, and 12 months for the hardener.

HEALTH AND SAFETY RECOMMENDATIONS:

According to Safety Data Sheet of Dangerous Substance for particular product.

PACKAGING

Item No	Capacity	Package, pieces	Package weight, kg
10503 (grey)	0,8 l		
10519 (white)	0,8 l		
10520 (black)	0,8 l		
10507 (hardener)	0,2l		
10503-0 (compl. primer. grey +hard.)	0,8+0,2 l		
10519-1 (compl. primer. white +hard.)	0,8+0,2 l		
10520-1 (compl. primer. black +hard.)	0,8+0,2 l		

This information is based on careful laboratory research and many years of experience. Strong market position does not absolve us from constant control of the quality of our products. However, we are not responsible for the final results after incorrect use of the product.



Sofia
6 "Andrey Germanov" str.
mobile: 089 666 3042 / 089 468 3880

Sofia, "Ovcha Kupel 1" quarter
33 "Promishlena" str., 429 bl., store 18,
mobile: 089 666 9071

Plovdiv
176 "Brezovsko shose" str.
mobile: 089 544 7503 / 089 666 3044

Varna
25 "Usta Kolyu Ficheto" str.
mobile: 089 666 9079 / 089 466 9023

Shumen, "Dobrudzhanski" quarter
Ind.zone, "Stroykomplekt" site
mobile: 089 455 1685 / 089 666 3043

Kardzhali
1 "Klokotnitsa" str.
mobile: 089 575 0749 / 089 666 3057

Troyan
49 "Makedoniya" str.
mobile: 089 666 9079 / 089 673 4489

Haskovo, 5 "Okolovrasten pat" str.
South Industrial zone
mobile: 089 666 3051 / 089 241 2833