


TECHNICAL DATA SHEET




Acrylic Clear Coat 2:1 VHS

Acrylic Clear Coat VHS FAST is a coat of very high content of solid particles, thanks to which it does not change its look when dried and it is characterized by high gloss and depth. To be used with all base coats available on the market, as well as with water bases. Good hardness and resistance to UV and weather conditions guarantee durability and gloss and depth ensure excellent look of the coat.

GROUND TYPE

Base coat.

MIXING RATIO



Clear coat
Hardener


By volume

2
1

By weight

100
50

SPRAYING VISCOSITY, NOZZLE, WORKING PRESSURE




DIN 4/20°C 17÷19 s, Ø1.3÷1.4 mm, 3÷4 bar

INSTRUCTION FOR USE



The coat shall be applied on previously sprayed and dried layers of a base coat.
Apply 1,5 of the coat.


EVAPORATION TIME



5 ÷ 10 min. between the coats (depending on temperature and thickness of the coat).

TECHNICAL DATA SHEET

DRYING TIME



10 minutes after the application of the last coat, it can be cured in higher temperature.

Dust free:

30 min in 20°C or 5 min in 60°C.


Usable hardness:

10 hours in 20°C or 30 min in 60°C.

Complete hardness:

after 7 days in 20°C.

POT LIFE ONCE MIXED WITH HARDENER



about 45 min. in the temperature of 20°C.

THICKNESS OF THE COAT

Single dry coat: 30-35 µm

EFFICIENCY

1 litre of the coat + hardener in adequate proportion allows obtaining about 10,5 m² of a dry coat 50µm thick.

CONTENT OF VOLATILE ORGANIC COMPOUNDS

VOC II/B/d limit =420g/L (for ready to use mixture)

VOC= 415g/L

STORAGE CONDITIONS

Store in a dark and cool place away from fire and heat sources. The shelf life in original package in the temperature of 20°C is 24 months for the coat and 12 months for the hardener.

TOOLS CLEANING

Thinner for nitrocellulose products or Thinner for acrylic products RANAL.

HEALTH AND SAFETY RECOMMENDATIONS

According to Material Safety Data Sheet of Dangerous Substance for particular product.

TECHNICAL DATA SHEET**PACKAGING**

Art. No	Capacity, L	Package, pieces:	Package weight, kg:
31202	1	6	7,10
31203	5	4	22,30
30711	hard. 0,5	6	3,20
30712	hard. 2,5	4	10,20

This information is based on careful, laboratory research and our long-standing experience. Strong market position does not absolve us from constant control of the quality of our products. However, we are not responsible for the final results after incorrect use of the product.



• Ж И В О Т В Ц В Е Т О В Е •
www.adacolor-bg.com

гр. София ул. „Андрей Германов“ 6 GSM: 089 666 3042 / 089 468 3880	гр. София, кв. Овча Купел 1, ул. „Промислена“ 33, бл.429, маг. №18 GSM: 089 666 9071	гр. Пловдив ул. „Брезовско шосе“ 176 GSM: 089 544 7503 / 089 666 3044	гр. Варна ул. „Уста Кольо Фичето“ 25 GSM: 089 666 9079 / 089 466 9023
гр. Шумен, кв. Добруджански, инд. зона: база на Стройкомплект GSM: 089 455 1685 / 089 666 3043	гр. Кърджали ул. „Клокотница“ 1 GSM: 089 575 0749 / 089 666 3057	гр. Троян ул. „Македония“ 49 GSM: 089 666 9079 / 089 673 4489	гр. Хасково, Южна индустриална зона, ул. „Околовръстен път“ 5 GSM: 089 666 3051 / 089 241 2833