

PALINAL

High Technology Paint

223ULTRA

ULTRA RAPIDO ARIA FORNO

ULTRA RAPID OVEN AIR

2004/42/IIB (d) (420) 420

PREPARAZIONE

Preparazione | Preparazione
Preparazione | Preparazione



RAPPORTO MISCELA

Mixing ratio | Relación de Mezcla
Proportion de melange | Mischverhältnis

2 : 1

PRODOTTO

Product | Producto | Produit | Produkt

223ULTRA

100 (Vol)

CATALIZZATORE

Hardener | Catalizador | Catalyseur | Katalysator

293.R010 rapido
293.R020 standard
293.R030 lento

50 (Vol)

DILUENTE

Thinner | Diluyente | Diluant | Verdunner

-

-

PRODOTTO PRODUCT PRODUIT PRODUCTO PRODUKT 223ULTRA	CATALISI CATALYS IS CATALYSE CATALISIS KATALYSE 293.R010 - 293.R020 - 293.R030	DILUIZIONE DILUTION DILUTION DILUCION VERDÜNNUNG -
--	--	--

50 g	25 g	
100 g	50 g	
150 g	75 g	
200 g	100 g	
250 g	125 g	
300 g	150 g	
350 g	175 g	
400 g	200 g	
450 g	225 g	
500 g	250 g	
600 g	300 g	
700 g	350 g	
800 g	400 g	
900 g	450 g	
1000 g	500 g	

I dati si riferiscono all'applicazione Standard | Data refer to standard application | Les données se réfèrent à l'application standard | Los datos se refieren a la aplicación Standard | Die Daten beziehen sich auf die Standardanwendung

APPLICAZIONE		
Applicazioni Applicazione Applicazioni Applicazioni		
	POT Pot life (20° C) Vie en pot (20° C) Topfzeit (20° C)	1,5 h
	VISCOSITÀ APPLICAZIONE Spraying viscosity Viscosidad de aplicación Viscosité d'application Verarbeit viscositat	18' ± 1 DIN4
	REGOLAZIONE DELLA PISTOLA Airbrush adjustment ajuste del aerógrafo réglage à l'aérographe Airbrush-Einstellung	2 Giri Turns Tours Vuelas Umdrehungen
	UGELLO Nozzle Boquilla Buse Duse	1,2 - 1,3 mm Standard/HVLP/LVLP
	PRESSIONE ARIA Air Pressure presión de aire Pression d'application Luft	4 Standard 1,8 - 2,2 HVLP/LVLP
	NUMERO MANI Number of coats Numero de capas Nombre des couches Spritzegänge	2
	INTERVALLO TRA LE MANI Intervallo Intervallo Intervallo Intervallo	5 min

ESSICCAZIONE & RESA		
Carteggiatura Carteggiatura Carteggiatura Carteggiatura		
	APPASSIMENTO Flash time Tiempo de secado Desséchement Abluftzeit	5 min
	FUORI POLVERE Dry dust free Hors poussière Fuera polvo Staubtrocken	20 min
	PRONTO AL MONTAGGIO Ready to use Prêt pour le montage Listo para el montaje Montagefest	1,30 h - 2 h
	ESSIC. COMPLETA * Through drying 20°C Sec en profondeur Durchgetrocknet 60°C	4 - 5 h 10 min Effettivi Actual Time Effectives Reales Effektive
	IR - ONDE MEDIE IR - Medium Waves IR - Onde moyennes IR - Ondas medias IR - Mittlere Wellen IR - IRRADIANTI A GAS IR - Gas-fired radiant heaters IR - Radiants gaz IR - Radiantes a gas IR - Gas-Strahler	Non Consigliato Not Recommended Déconseillé No Recomendado Nicht Empfehlen
	LUCIDABILITA' Polishability at 20 °C Polissabilité à 20° C Pulido a 20°C Schleifbar bei 20°C Polishability at 60 °C Polissabilité à 60° C Pulido a 60°C Schleifbar bei 60°C	4 - 5 h 10 min Effettivi E Raffreddamento Actual Time And Cooling Effectives Et Refroidissement Reales Y Enfriamiento Effektive Und Abkühlung
	SPESSORE FILM SECCO Dry film thickness Espesor de la película seca Epaisseur du film sec Trockenschichtstärke	50 - 60 µ
	RESA RFU -M² / KG x 1 µ Yield RFU Rendement RFU Rendimiento RFU Ergiebigkeit RFU	500

* Per resistenze chimico/fisiche reticolazione completa a 20°C : 7 giorni |
For chemical/physical resistance full cross-linking at 20°C : 7 days |
Pour la résistance chimique/physique réticulation complète à 20°C : 7 jours |
Para resistencias químicas/físicas reticulación completa a 20 °C : 7 días |
Erhalt vollständiger chemischer und physikalischer Festigkeit nach kompletter Vernetzung bei 20 °C : 7 Tage

CONSERVABILITA' Ageing Tiempo de la conservación Conservabilità Haltbarkeit	
CONSERVABILITA' Ageing Tiempo de la conservación Conservabilità Haltbarkeit	24 mesi months meses mois Monaten 5°C < tC° > 35°C

PRODOTTI COMPLEMENTARI

| Complementary products | Produits complémentaires | Productos complementarios | Komplementäres Produkt

	CATALIZZATORE Hardener Catalyseur Catalizador Katalysator	DILUENTE Thinner Diluant Diluyente Verdünner
293.R020	Standard	
293.R010	Rapido Fast Rapide Rápido Schnell	
293.R030	Lento Slow Lent Lento Langsam	



• ЖИВОТ В ЦВЕТОВЕ •

www.adacolor-bg.com

гр. София ул. „Андрей Германов“ 6 GSM: 089 666 3042 / 089 468 3880	гр. София, кв. Овча Купел 1, ул. „Промислена“ 33, бл.429, мар. №18 GSM: 089 666 9071	гр. Пловдив ул. „Брезовско шосе“ 176 GSM: 089 544 7503 / 089 666 3044	гр. Варна ул. „Уста Кольо Фичето“ 25 GSM: 089 666 9079 / 089 466 9023
гр. Шумен, кв. Добруджански, инд. зона: база на Стройкомплект GSM: 089 455 1685 / 089 666 3043	гр. Кърджали ул. „Клокотница“ 1 GSM: 089 575 0749 / 089 666 3057	гр. Троян ул. „Македония“ 49 GSM: 089 666 9079 / 089 673 4489	гр. Хасково, Южна индустриална зона, ул. „Околовръстен път“ 5 GSM: 089 666 3051 / 089 241 2833